

YELLOW JACKET™

TECHNICAL DATA SHEET

Properties	ASTM	Units	Typical Value
Specific Gravity	D-1505		.906
Melt Flow	D-1238	g/10 min	.5
Tensile @ Yield	D-638	Psi	4,000
Flexural Modulus	D-790	Psi	195,000
Elongation @ Break	D-638	%	>500
HDT @ 66psi	D-648	°F	190
Notched Izod @73°F	D-256	Ft-lb/in	No Break
Rockwell Hardness	D-785	R Scale	75

Compiles with 21 CFR 177.1520 and Mil- P- 83668

Notice: All statements, information, and data given herein are believed to be accurate and reliable but are presented without guarantee, warranty, or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation of warranty that such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.